



Tested System : **Canadian UV System**

Weatherometer QUV-A

$\lambda = 340 \text{ nm}$


Method : **ASTM G 53 - SAE J 2020**

Cycle : **8h UV lamp at 70°C + 4h condensation at 50°C**

Reference:



Original aspect : Clear , water white transparent coating



After ageing :

After **75** hours